12-1008







For Standby Telecom Applications

CAPACITIES FROM 345 - 2180 AMPERE-HOURS



The msEndur II is the latest advancement in battery technology with enhanced features for TEL applications.

By combining the service life reliability of a flooded battery with the performance energy density of a valve-regulated battery, C&D has created the msEndur II — The True Long-Life Battery™.

The msEndur II series of batteries are unmatched in power density with space saving modular designs and have a 20-year design life to reduce the total cost of ownership.

With its much lower float current, the msEndur II yields significant electrical costs savings over its life making it the most environmentally 2V VRLA battery.

APPLICATIONS

- Wireless
- Wireline
- Central Office
- Mobile Switching Centers
- PBX Systems
- Microwave
- Broadband Headend
- Network Operation Ctrs
- Data Centers

FEATURES & BENEFITS

ADVANCED SYSTEM FEATURES

- Modular design for ease of installation and stacking flexibility
- Space saving design for the greatest amount of power in a small footprint
- Certified as NEBS Level 3 and compliant to Earthquake Risk Zone 4 in various system configurations
- Exceeds 1997 UBC Zone 4 seismic requirements for at or below grade installations
- Exceeds 2000/2003 IBC requirements for 125% g level
- Tin-plated copper alloy connectors minimize maintenance
- New Ohmic Ring™ for ease of maintenance readings. With specially adapted probes only one technician is required to take readings.

ADVANCED MATERIALS

- Advanced micro-porous <u>A</u>bsorbed <u>G</u>lass <u>M</u>at separators for ultra-low float current — reduces grid corrosion for a long, usable service life
- Proprietary calcium alloys to minimize positive grid corrosion and growth maximizes battery life
- Robust polypropylene container and cover — enhances product quality and improves strength of materials for safe operation with flammability rating UL94 VO, LOI>28%

 Highly efficient, proprietary plate processing for high utilization of active material — results in high energy density and low float current

ADVANCED PROCESSES

- Advanced formation process results in a narrow float voltage window making on-site float matching unnecessary
- Highly controlled manufacturing processes for exceptional and consistent plate quality

ADVANCED SERVICE LIFE & WARRANTY

- Proprietary cell design and manufacturing process provides for 20 year design life and documented long-lasting service life
- · Industry leading warranty

ADVANCED EXPERIENCE

- Over 100 years of experience in the battery industry
- The only producer and marketer of complete battery and electronics systems for total power solutions
- Fully backed by a worldwide network for local service

Constant Current Discharge Ratings

AMPERES @ 77°F (25°)											
FV/CeII	Models	1 hr	2 hr	3 hr	4 hr	5 hr	6 hr	8 hr	10 hr	12 hr	24 hr
	AT-07P	189	123	93	75	63	55	43	36	30	16
	AT-09P	259	170	129	104	88	76	60	50	42	23
	AT-11P	324	213	161	130	110	95	75	62	53	28
	AT-13P	352	228	172	139	117	101	80	66	56	30
	AT-15P	454	298	225	182	154	133	105	87	74	40
	AT-17P	505	327	247	200	168	145	115	95	81	43
	AT-19P	583	383	290	234	198	171	135	112	95	51
1.75	AT-21P	631	409	309	250	210	182	144	119	101	54
	AT-23P	713	468	354	287	241	209	165	136	116	62
	AT-25P	757	491	370	299	252	218	172	143	122	65
	AT-27P	843	553	418	339	285	247	195	161	138	73
	AT-29P	884	573	432	349	294	255	201	166	142	76
	AT-35P	1102	723	547	443	373	323	255	211	180	96
	AT-39P	1199	777	586	474	399	345	273	226	193	103

Constant Power Discharge Ratings

KILOWATTS PER CELL @ 77°F (25°C)										
FV/CeII	Models	1 min	5 m in	10 min	15 min	20 min	30 min	45 m in	1 hr	
	AT-07P	0.837	0.791	0.730	0.669	0.612	0.520	0.430	0.373	
	AT-09P	1.117	1.055	0.973	0.892	0.816	0.693	0.574	0.497	
	AT-11P	1.396	1.318	1.217	1.115	1.020	0.866	0.717	0.622	
	AT-13P	1.558	1.471	1.358	1.244	1.138	0.967	0.800	0.694	
	AT-15P	1.954	1.846	1.704	1.561	1.427	1.213	1.004	0.870	
	AT-17P	2.233	2.110	1.947	1.784	1.631	1.386	1.147	0.995	
1.67	AT-19P	2.512	2.373	2.190	2.007	1.835	1.559	1.291	1.119	
1.07	AT-21P	2.792	2.637	2.434	2.230	2.039	1.733	1.434	1.243	
	AT-23P	3.071	2.901	2.677	2.452	2.243	1.906	1.578	1.368	
	AT-25P	3.350	3.164	2.920	2.675	2.447	2.079	1.721	1.492	
	AT-27P	3.629	3.428	3.164	2.898	2.651	2.253	1.864	1.617	
	AT-29P	3.908	3.692	3.407	3.121	2.855	2.426	2.008	1.741	
	AT-35P						2.946	2.438	2.114	
	AT-39P							2.725	2.363	


Please refer to the msEndur II Stackable Module System with Module Dimensions and Weights brochure, 12-1014, for a listing of typical msEndur II Module Systems dimensions and weights.


Please refer to the **msEndur II Performance Specifications Brochure**, **12-1015**, for an expanded list of constant power and constant current ratings and end voltages.

You may also access the product ratings by logging onto the **C&D Battery Sizing Program** at **www.cdstandbypower.net**

Specifications and Characteristics

Cells, Voltage per Unit						1 cell, 2 VDC								
Recommended Operating Temperature					77°F (25°C)									
Connection Torque:					Initial: 160 ir	n-lbs (18 N-m), Re-torque	: 125 in-lbs (1-	4 N-m)					
Recommended Float Charging Voltage (ATL Recommended Float Voltage)					AT-P = 2.25 - 2.27 volts per cell average @ 77°F (25°C) ATL-P = 2.17 - 2.22 volts per cell average @ 77°F (25°C)									
Charger Compensation Temperature / Voltage				(-)2 mV/cell/°F above 77°F (-3.6 mV/cell /°C above 25°C) +2 mV/cell/°F below 77°F (+3.6 mV/cell /°C below 25°C)										
	AT-07P ATL-07P	AT-09P ATL-09P	AT-11P ATL-11P	AT-13P ATL-13P	AT-15P ATL-15P	AT-17P ATL-17P	AT-19P ATL-19P	AT-21P ATL-21P	AT-23P ATL-23P	AT-25P ATL-25P	AT-27P ATL-27P	AT-29P ATL-29P	AT-35P ATL-35P	AT-39P ATL-39P
Number of														
Terminals	2	2	2	2	2	2	4	4	4	4	4	4	4	4
8 Hr AH Rate to 1.75 v/c @ 77°F (25°C)				2 640 / 515				1150 / 980			1560 / 1270		2040 / 1660	






Modules

msEndur II cells are designed to be mounted in stackable modules of either 3, 4, 5, 6, 8 &10 cells. The most popular module sizes and configurations for Telecom systems are:

	AT-07P through AT-21P	AT-15P through AT-39P
Cells Wide/Module	6	3
Modules High	4	8

The specific cell wide x module high system configuration is flexible and can be configured to best match the physical requirements of the customer's site.

Detailed system dimensions and combinations are available in the **msEndur II Module Brochure 12-1014.**



Service Life - Reliability

The msEndur II is the latest advancement in battery technology. By combining the service life reliability of a flooded battery with the performance energy density of a valve-regulated battery C&D has created the msEndur II — The True Long-Life Battery™. The msEndur II series of batteries are unmatched in power density with space saving modular designs and have a 20-year design life to reduce the total cost of ownership.



The msEndur II VRLA battery is the environmentally friendly battery that saves you money in normal operation.

The same low float current that ensures a twenty year life, is good for the environment and saves money

- Up to 75% lower float current
- Consumes up to 75% less electricity
- Lower float current generates less heat
- · Less heat generated reduces required air conditioning
- Less electricity consumed in float charging and air conditioning = reduce carbon emissions

Go to www.cdtechno.com/savings to check out your possible savings



1400 Union Meeting Road P.O. Box 3053 • Blue Bell, PA 19422-0858 (215) 619-2700 • Fax (215) 619-7899 • (800) 543-8630 customersvc@cdtechno.com www.cdtechno.com Any data, descriptions or specifications presented herein are subject to revision by C&D Technologies, Inc. without notice. While such information is believed to be accurate as indicated herein, C&D Technologies, Inc. makes no warranty and hereby disclaims all warranties, express or implied, with regard to the accuracy or completeness of such information. Further, because the product(s) featured herein may be used under conditions beyond its control, C&D Technologies, Inc. hereby disclaims all warranties, either express or implied, concerning the fitness or suitability of such product(s) for any particular use or in any specific application or arising from any course of dealing or usage of trade. The user is solely responsible for determining the suitability of the product(s) featured herein for user's intended purpose and in user's specific application.